

## UniPlast 106

### Cement-based, pre-blended thrown coat render

#### Description

**UniPlast 106** is a cement-based, factory pre-blended thrown coat render. It is especially formulated to be applied by hand as an undercoat render (key coat) for walls and ceilings.

#### Features and benefits

- Ready to use. Just requires the addition of water.
- Factory controlled production to give a consistently high-quality product
- Suitable for internal and external applications.
- Good resistance to extreme weather conditions including coastal areas.
- Improved bond strength.

#### Recommended for

**UniPlast 106** is used as a rough bonding coat (key coat) in multi coat render system. It should be applied onto walls and ceilings prior to the application of cement-based plaster. **UniPlast 106** can be thrown by hand or can be sprayed using suitable spraying machine. The suitable substrates are traditional concrete, engineered concrete blocks and different types of masonry and bricks.

#### Composition

**UniPlast 106** is composed of high strength Portland cement, selected well graded fillers and compound of selected chemicals to improve adhesion and workability.

#### Packaging

**UniPlast 106** is available in 25 kg bags.

#### Coverage

When applied at 5 mm thick, coverage is approximately 9 kg/m<sup>2</sup>.

#### Note:

Coverage rate takes no account of wastage and may vary according to surface condition and application method.

#### Technical data

Mixed density	1.85 kg/liter
Compressive strength	>25 N/mm <sup>2</sup>
Tensile adhesion strength	>0.5 N/mm <sup>2</sup>
Pot life	60 minutes @20°C
Application thickness	5 – 8 mm/coat
Appearance	Grey powder

#### Surface preparation

All surfaces must be sound, clean, dry and free of any material which may impair adhesion. Scaffolding must be independently tied to allow for uninterrupted application.

Any faults in the structure, particularly those which may lead to moisture penetration must be rectified.

Expansion joints should be included as required by the substrate and carried through all applied materials.

High suction substrates should be evenly dampened with clean water prior to the application of **UniPlast 106**. Remove any excess water at the time of application.

#### Mixing

**UniPlast 106** mortar can be obtained by mixing a 25 kg bag of **UniPlast 106** with approximately 8-9 liters of clean water. For best results, use as little water as possible and mix to give a workable consistency.

Mix mechanically in a suitable batch mixer. A slow speed drill fitted with suitable mixing paddle can also be used. Add the contents of **UniPlast 106** bag to the mixing water slowly while mixing. Mix for 5-10 minutes until a thick slurry (wetter mortar) consistency mortar is achieved. Do not over mix.

MIX AND USE. Mix material that can be applied within 60 minutes (pot life).

#### Application

Throw **UniPlast 106** by hand immediately onto the prepared substrate. Another application method is to apply **UniPlast 106** using spraying machine. Spray UniPlast 106 through 3-4 mm nozzle at 3-5 bar pressure.

The final surface of **UniPlast 106** should be rough enough to bond the following cement base plaster.

Allow to dry and shrink completely before subsequent applications. This will depend on weather conditions, but normally requires a minimum of 36 hours.

## Curing

As with all cement-based products, good curing is very important to ensure that the optimum characteristics are obtained. Always cure with tap water for at least 2 – 3 days. Begin curing as soon as the final setting is achieved. The applied areas should be protected from direct sunlight and heavy wind. In cold, humid or unventilated areas, it may be necessary to leave the application for a longer curing period.

## Important notes

### Do not apply:

- In damp/wet conditions.
- In temperatures below 5°C or above 30°C.
- On elevations in direct sunlight or where the substrate is hot.

## Finishing

Key coat made with **UniPlast 106** can be filled with **UniPlast 125/125F** base coat (or jobsite sand/cement render) to have an even surface as per project's specification.

## Cleaning

Clean tools with water immediately after use. Hardened materials should be cleaned mechanically.

## Storage and shelf life

If stored unopened in a dry place at a temperature between +5°C and +30°C away

from sources of heat and moisture, shelf life is 12 months from the date of manufacture printed on the pack.

## Health and Safety

This product contains cement which may cause skin irritation. It may cause allergic skin reaction and eye damage. Avoid breathing dust. Wear protective gloves, eye goggles and clothing. In case of skin contact, wash with plenty of water. In case of eye contact, rinse continuously with water for several minutes and seek medical attention. Dispose excess material to special waste collection point in accordance with local & national regulation. Keep out of reach of children.

For further information, please ask for Safety Data Sheet for this product.

***The most up-to-date TDS can be obtained from ACC Customer Service Department, or downloaded from our website: [www.acc.com.eg](http://www.acc.com.eg).***

## More from ACC

A wide range of construction chemicals, specialty mortars and specialized building materials are manufactured by ACC which include:

- Waterproofing.
- Flooring.
- Tile Adhesives & Grouts.
- Concrete Repair.
- Non-Shrink Grouts.
- Bonding Agents.
- Exterior Façade Coatings.
- Premixed Fairing Coats, Renders & Mortars.
- Putties (stucco).
- Sealers & Emulsion Paints.